

## Appendix 3: Material Parameters

Name	Symbol	Germanium	Silicon	GaAs
Bandgap energy at 300 K	$E_g$ (eV)	0.66	1.12	1.424
Breakdown Field	$E_{br}$ (V/cm)	$10^5$	$3 \times 10^5$ *	$4 \times 10^5$
Density	(g/cm <sup>3</sup> )	5.33	2.33	5.32
Effective density of states in the conduction band at 300 K	$N_c$ (cm <sup>-3</sup> )	$1.02 \times 10^{19}$	$2.82 \times 10^{19}$	$4.35 \times 10^{17}$
Effective density of states in the valence band at 300 K	$N_v$ (cm <sup>-3</sup> )	$5.65 \times 10^{18}$	$1.83 \times 10^{19}$	$7.57 \times 10^{18}$
Intrinsic concentration at 300 K	$n_i$ (cm <sup>-3</sup> )	$2.8 \times 10^{13}$	$1.0 \times 10^{10}$	$2.0 \times 10^6$
Effective mass for density of states calculations				
Electrons	$m_e^* / m_0$	0.55	1.08	0.067
Holes	$m_h^* / m_0$	0.37	0.81	0.45
Electron affinity	$\chi$ (V)	4.0	4.05	4.07
Lattice constant	$a$ (pm)	564.613	543.095	565.33
Mobility at 300 K (undoped)				
Electrons	$\mu_n$ (cm <sup>2</sup> /V-s)	3900	1400 <sup>†</sup>	8800
Holes	$\mu_p$ (cm <sup>2</sup> /V-s)	1900	450 <sup>†</sup>	400
Effective mass for conductivity calculations				
Electrons	$m_e^* / m_0$	0.12	0.26	0.067
Holes	$m_h^* / m_0$	0.21	0.386	0.34
Relative dielectric constant	$\epsilon_s / \epsilon_0$	16	11.9	13.1
Thermal conductivity at 300 K	$\chi$ (W/cmK)	0.6	1.5	0.46
Refractive index at 632.8 nm wavelength	$n$	5.441	3.875	3.856
		- i 0.785	- i 0.0181	- i 0.196

\* See also section 4.5.1: Breakdown field in silicon at 300 K

† See also section 2.7.2: Mobility of doped silicon at 300 K